



Linseed Oil & Derivatives

亚麻油和衍生物

TECHNICAL DATA SHEET

技术指标参数

PRODUCT PROPERTIES - 产品性能	Raw Linseed Oil 粗亚麻油	Refined Linseed Oil 精炼亚麻油	Double Boiled Linseed Oil 双沸制亚麻油	Pale Boiled Linseed Oil 沸制亚麻油	Linseed Stand Oil 熟亚麻油
Colour - 色度 (Gardner)	13 Max	4 Max	12 -16	10 Max	7 Max
Acid Value - 酸值 (mgKOH/g)	3 Max	0.5 Max	5 Max	4 Max	12 Max
Iodine Value - 碘值 (gI ₂ /100g)	175 Min				
Saponification Value - 皂化值 (mgKOH/g)	185-195	185-195	190-215		
Refractive Index - 折光指数 20° C	1.478-1.485	1.478-1.485			
Density - 密度 15.5°C (g.cm ⁻³)	Appr 0.934	Appr 0.934	Appr 0.940		
Viscosity - 粘度 20°C		Appr. 50 mPa.s	0.7 Poise Min	0.7 Poise Min	114-126 Poise Min
Ash - 灰度 %	0.15 % Max				
Volatile - 挥发性 20°C	0.2 % Max				
Drying Time - 干燥时间 (Hrs)			14 Max	14 Max	

Packing 包装 - 190kg Reconditioned Steel Drums / IBC / Disposable Flexi bags / ISO Tanks

Origin & Shipment 原产地&装运地 - Belgium 比利时

Swisloyd Pty Limited

Suite 104, 20 Lexington Drive
Bella Vista, NSW 2153, Australia

Tel: (61) 2 9476 3345
Fax: (61) 2 9477 2867

Swisloyd Limited

30-03, East Tower, World Trade Center
Colombo 00100, Sri Lanka

Tel: +94 (11) 55 77 600
Fax: +94 (11) 55 77 699

Guangzhou Xing Mai Long Commerce & Trade Co Ltd

2215, Fu Li Ying Feng Mansion
No. 2, Huaqiang Road, Zhujiang Xin Cheng
Tianhe, Guangzhou, Guangdong, China

Tel: +86 (20) 3867 8770
Fax: +86 (20) 3867 8330

www.swisloyd.com
welcome@swisloyd.com

Swisloyd Limited

Regency House, Westminster Place
York Business Park, Nether Poppleton
York, YO26 6RW.

Swisloyd Inc

3502 Katella Avenue, Suite 207
Los Alamitos, CA 90720, USA

Tel: +1 562 430 8538
Fax +1 562 430 8548