



# Petroleum Resin

## 碳九石油树脂

TECHNICAL DATA SHEET  
技术指标参数

PRODUCT PROPERTIES - 产品性能	C9-7	C9-8	C9-10	C9-12
Appearance - 外观	Light Yellow Flakes / Granular - 淡黄色片状 / 颗粒			
Softening Point - 软化点 °C	111 - 120			
Colour (Gardner) - 色度 Sample: Toluene = 1:1	7 Max	8 Max	10 Max	12 Max
Bromine Value - 溴值	45 Max	60 Max	60 Max	60 Max
Acid Value - 酸值 (mgKOH/g)	0.5 Max			
PH Value - PH 值	5 - 8			
Ash Content - 灰度含量	0.1%			
Water Content - 水含量	0.001% Max			

**Packing 包装** - 25 Kg PP Bags 聚丙烯内衬纸袋

**Origin & Shipment 原产地&装运地** - China 中国

### Swisloyd Pty Limited

Suite 104, 20 Lexington Drive  
Bella Vista, NSW 2153, Australia

Tel: (61) 2 9476 3345  
Fax: (61) 2 9477 2867

### Swisloyd Limited

30-03, East Tower, World Trade Center  
Colombo 00100, Sri Lanka

Tel: +94 (11) 55 77 600  
Fax: +94 (11) 55 77 699

### Guangzhou Xing Mai Long Commerce & Trade Co Ltd

2215, Fu Li Ying Feng Mansion  
No. 2, Huaqiang Road, Zhujiang Xin Cheng  
Tianhe, Guangzhou, Guangdong, China

Tel: +86 (20) 3867 8770  
Fax: +86 (20) 3867 8330

[www.swisloyd.com](http://www.swisloyd.com)  
[welcome@swisloyd.com](mailto:welcome@swisloyd.com)

### Swisloyd Limited

Regency House, Westminster Place  
York Business Park, Nether Poppleton  
York, YO26 6RW.

### Swisloyd Inc

3502 Katella Avenue, Suite 207  
Los Alamitos, CA 90720, USA

Tel: +1 562 430 8538  
Fax +1 562 430 8548